

## ROOFCOTE<sup>™</sup> SUPA COOL<sup>™</sup> SYSTEM

*Roofcote Supa Cool* is a revolutionary heat reflective roof membrane coating system that reduces the heat build up of a roof surface due to sunlight. *Supa Cool* combines Thermilate® insulating ceramic beads with specially engineered ceramic pigments that reflect radiant heat.

Supa Cool provides an attractive, durable roof coating in a range of 26 colours using our Reflectacoat Tint Pacs. The even flow and attractive gloss level improve the condition and appearance of the roof, and the coating system provides long-term weather protection.

A conventional primer from the Acryloc Primerbond family is applied first, followed by *Supa Cool Thermicoat* and then *Supa Cool Membrane*.

Thermilate® insulating ceramic beads are supplied by Biotech Australasia, see [www.thermilate.com.au](http://www.thermilate.com.au)

Heat Reflective pigments are supplied by Shepherd Color, see [www.shepherdcolor.com](http://www.shepherdcolor.com) for “Arctic” colours and Ferro Corporation, see [www.ferro.com](http://www.ferro.com) for “Cool Colours”.

More information on Heat Reflective coatings is available at <http://eetdnews.lbl.gov/nl19/cool.htm>

The *Roofcote Supa Cool* system includes a full range of components for coating commonly encountered roof substrates. The coating system is fully covered by the Acryloc Manufacturer’s Warranty.

Suitable substrates include:

- Concrete tiles
- **Unglazed** Terracotta tiles
- Zinalume®
- Colorbond®
- Galvanised Iron
- Fibre Cement Sheeting

The key products in the *Roofcote Supa Cool* system are listed below:

| Product                           | Purpose / Notes  |
|-----------------------------------|--|
| <b>↳ Repointing</b>               |  |
| Ridgepoint                        | Flexible Pointing Compound for use on concrete & terracotta roofs      |
| <b>↳ Surface Preparation</b>      |  |
| Acryloc Heavy Duty Cleaner        | Applied before pressure cleaning to assist dirt, moss & lichen removal |
| Acryloc Mould Rid                 | Leave on mould inhibitor, applied after cleaning & before priming      |
| Acryloc Rust Converter            | For passivation & removal of light rust from metal roof sheeting       |
| <b>↳ Prime Coat</b>               | Essential for adhesion of the coating system.                          |
| Acryloc Primerbond                | For Concrete, Fibre cement, aged Colorbond® & unglazed Terracotta      |
| Acryloc Metal & Galv Primer       | For Zinalume & Galvanised Iron   |
| <b>↳ Build Coat (if required)</b> |  |
| Acryloc High Build Undercoat      | Optional, smooth badly weathered concrete tiles before top coat        |
| <b>↳ Thermicoat<sup>™</sup></b>   |  |
| Supa Cool Thermicoat              | One coat over Prime Coat or High Build Undercoat.                      |
| <b>↳ Membrane Coat</b>            |  |
| Supa Cool Membrane                | One coat over Thermicoat.  |

Disconnect guttering from Rainwater tanks / Stormwater systems before commencing work, **see p 9, Important Notes.**

### **Limitations.**

The *Roofcote Supa Cool* system is **NOT** suitable for coating partly or fully glazed Terracotta tiles.

### **Also Available:**

Cement Renders, Texture Coats, Exterior Paints, Interior Acrylic paints, Liquid Pigment, Tools & Consumables

## SUPA COOL™ TEN YEAR SYSTEM WARRANTY

---

Acryloc Building Products provides a material replacement warranty against bubbling, peeling or flaking of the full Roofcote Supa Cool System caused by any defect in manufacture for a period of ten years from the date of application, provided that:

- the products have been applied correctly by a skilled and experienced applicator in accordance with all current application criteria as specified by Acryloc Building Products; and,
- the products have been stored in accordance with current criteria and have been used within the recommended shelf life period.

The liability of Acryloc Building Products pursuant to this warranty is limited to re-supply of the coating materials.

The Applicator provides a separate warranty for the application and workmanship.

Acryloc Building Products is not liable under this warranty for:

- damage or failure caused by movement of the substrate or structure;
- damage or failure caused by structural cracking;
- damage or failure caused by hydrostatic pressure or entrapped moisture;
- damage or failure caused by maltreatment, such as mechanical damage, whether during installation or at a subsequent time;
- damage or failure caused by faulty design and/or construction;
- variations in colour, strength, appearance or workability resulting from on-site mixing procedures and conditions.

This warranty is provided in lieu of all other warranties, whether expressed or implied, and all other obligations on the part of Acryloc Building Products apart from any warranties or conditions which arise by operation of law and which may not be negated or modified.

---

### ACRYLOC BUILDING PRODUCTS:

- has been manufacturing water based coatings for exterior use for almost twenty years;
- supplies customers throughout Australia as well as export markets including New Zealand and China;
- is part of the Bramalco/Modern Group, a privately owned set of companies turning over \$100+ million per year;
- factory and head office are located in Dry Creek, a suburb on the northern edge of Adelaide;
- all roof coating products are made in our factory.

## Product Technical Data & Specifications

### RIDGEPOINT<sup>®</sup>

| PRODUCT TYPE      | PACKAGING                   | NOMINAL WEIGHT |
|-------------------|-----------------------------|----------------|
| Flexible Pointing | 10L Heavy Duty Plastic Pail | 16.5kg         |

Ridgepoint consists of a flexible acrylic base blended with carefully graded aggregates and various additives and is supplied in a range of pre-mixed colours. Independent testing shows that Ridgepoint exceeds the criteria for C3 wind uplift in AS2050 - 1995 INSTALLATION OF ROOF TILES, APPENDIX F.

#### MAIN USES

*Ridgepoint* is as a ready to use, pre-coloured pointing compound which flexes with movements in the roof structure, while remaining strong and crack resistant. This provides a convenient and consistent alternative to traditional cement and sand based pointing mortar.

*Ridgepoint* may be used for new tiled roofs, re-ridging of aged roofs or as part of the CRC system for roof restorations.

#### SUITABLE SUBSTRATES

- Bedding mortar on concrete or terracotta roof tiles

#### SUBSTRATE PREPARATION

- New bedding mortar should be applied with a bedding frame to prevent holes under the capping. Any holes which are present must be filled with mortar and the mortar allowed to dry before pointing
- Bedding mortar should be struck off straight, not at an angle to the cap. Weep holes must be used as per the tile manufacturer's specifications
- Allow a minimum of 24 hours fine weather for the bedding mortar to cure before pointing
- Existing bedding requiring re-pointing or repair must be clean & sound. Clean by thoroughly wire brushing & hosing down as a minimum – pressure cleaning is the recommended method.

#### APPLICATION

- Acryloc Extenda can be added in warmer conditions to slow down the drying time (30-40 ml per pail & mix well)

#### Method

- Mix thoroughly with a pointing trowel or power mixer. *Ridgepoint* does not require thinning or dilution
- *Ridgepoint* should be applied to the capping with a steel trowel to a thickness of 3-5mm
- *Ridgepoint* must cover all the bedding material and the edge of the ridge-cap
- *Ridgepoint* may be over coated once cured using the appropriate components selected from the CRC<sup>™</sup> system

#### Important Notes

- Do not apply *Ridgepoint* on exposed surfaces when rain is anticipated within 5 hours of completion of the work, longer in damp, cold +/- humid conditions. If rain is likely overnight, ridge covers should be used

#### Clean-Up

Clean up with water

#### TECHNICAL DATA

|                                      |  |          |             |
|--------------------------------------|--|----------|-------------|
| APPEARANCE                           | Viscous, Coloured Gritty Paste                                       |          |             |
| ODOUR                                | Low  |          |             |
| SPECIFIC GRAVITY (NOMINAL)           | 1.4 -1.7   |          |             |
| THEORETICAL COVERAGE                 | 25-30 linear metres per pail at 3-5mm, 40-60 caps subject to profile |          |             |
| WET FILM THICKNESS (RECOMM)          | 3-5mm single coat  |          |             |
| DRY FILM THICKNESS (MIN)             | N/A  |          |             |
| DRY TIME (25°C & 50% RH)<br>(APPROX) | Tack Free  | Overcoat | Fully Dried |
|                                      | 30 mins  | 24 hours | N/A         |

## Product Technical Data & Specifications

### ACRYLOC<sup>®</sup> HEAVY DUTY CLEANER

| PRODUCT TYPE | PACKAGING                   | NOMINAL WEIGHT |
|--------------|-----------------------------|----------------|
| Preparation  | 20L Heavy Duty Plastic Pail | 22.5kg         |

Acryloc Heavy Duty Cleaner is a high grade product designed specifically for releasing moss, lichen, and minor deposits of grease and oil from various substrates to make subsequent pressure cleaning faster and more effective.

Acryloc Heavy Duty Cleaner is supplied as a concentrate and must be diluted before use.



#### SUITABLE SUBSTRATES

- Roofing tiles
- Cement Render
- Ceramic tiles
- Fibre Cement Sheeting
- Clay and Concrete Brickwork
- Driveways & paths

#### APPLICATION

- Acryloc *Heavy Duty Cleaner* is an alkaline, corrosive liquid which may produce severe burns & skin irritation.
- Diluted cleaner must be stored in plastic containers.
- Acryloc *Heavy Duty Cleaner* may attack some surfaces such as aluminium. Test on a small area first.

**Dilution– always add Acryloc *Heavy Duty Cleaner* to water, do NOT add water to *Heavy Duty Cleaner***

Acryloc *Heavy Duty Cleaner* must be diluted before use (hot water must not be used)

- Light to medium duty cleaning (mud, light soiling, road grime, normal roof cleaning)
  - Add 25mls of Acryloc *Heavy Duty Cleaner* to 1Lt of clean water before use
- Heavy duty cleaning (moss, lichen, oils, grease)
  - Add 100ml of Acryloc *Heavy Duty Cleaner* to 1Lt of clean water before use
- **Roof Areas**
  - **Disconnect rainwater collection, see page 9, Important Notes.**
  - Application with a garden type weed sprayer is recommended
  - Apply liberally, leave for 1-2 hours, overnight for heavy moss growth, then pressure clean
  - Acryloc *Heavy Duty Cleaner* must be completely removed prior to painting the cleaned surface.

#### Coverage

10-15m<sup>2</sup>/L per coat at normal dilution

#### Clean-Up

Clean up with water

#### TECHNICAL DATA

|                            |                               |
|----------------------------|-------------------------------|
| APPEARANCE                 | Watery yellow liquid          |
| ODOUR                      | Low                           |
| APPLICATION METHODS        | Roller, brush, spray          |
| SPECIFIC GRAVITY (NOMINAL) | ~1.04                         |
| NO. OF COATS               | As required, typically 1 coat |

## Product Technical Data & Specifications

### ACRYLOC<sup>®</sup> MOULD RID

#### PRODUCT TYPE

Preparation Products

#### PACKAGING

20L Heavy Duty Plastic Pail

#### NOMINAL WEIGHT

21.5kg

Acryloc *Mould Rid* is a broad spectrum water based biocide which inhibits the growth of moss and lichen on surfaces to which it is applied.

Acryloc *Mould Rid* is available as a concentrate and in a ready to use form. For ease of identification, the concentrate packaging has an orange coloured label.

Acryloc *Mould Rid* may be applied to clean cement and unglazed terracotta roofs, and to a range of other substrates, to inhibit the subsequent growth of moss and lichen. Acryloc *Mould Rid* is applied prior to priming.

#### SUITABLE SUBSTRATES

- Pre-cleaned unglazed terracotta tiles
- Colorbond®
- Galvanised Iron
- Cement Render
- Tilt panel walls
- Pre-cleaned cement tiles
- Zinalume®
- Fibre Cement Sheeting
- AAC (Autoclaved Aerated Concrete)
- Brickwork

#### APPLICATION

**Disconnect rainwater collection, see page 9, Important Notes.**

Acryloc Mould Rid **Ready To Use**

- *Mould Rid ready to use* can be applied straight from the pail

Acryloc Mould Rid **Concentrate**

- Acryloc *Mould Rid Concentrate* (orange label) must be diluted with before use
- For normal use - Add (1) part Acryloc *Mould Rid Concentrate* to twenty (20) parts of clean water (1:20)
- For severe growth areas – Add one (1) part Acryloc *Mould Rid Concentrate* to ten (10) parts of clean water (1:10)
- If applying on roofs, application with a garden type weed sprayer is recommended. Acryloc *Mould Rid* can also be applied using a roller, brush, pad, HVLP spray equipment or airless spray equipment.
- Apply enough Acryloc *Mould Rid* to adequately “wet” the surface.
- Allow to dry, do wash off. Re application will be necessary if rainfall occurs before Acryloc *Mould Rid* is overcoated.

#### Coverage

10-15m<sup>2</sup>/L per coat when diluted

#### Clean-Up

Clean up with water

#### TECHNICAL DATA

|                                      |                      |          |             |
|--------------------------------------|----------------------|----------|-------------|
| APPEARANCE                           | Watery bluish liquid |          |             |
| ODOUR                                | Low                  |          |             |
| APPLICATION METHODS                  | Roller, brush, spray |          |             |
| SPECIFIC GRAVITY (NOMINAL)           | ~ 1.0                |          |             |
| DRY TIME (25°C & 50% RH)<br>(APPROX) | Tack Free            | Overcoat | Fully Dried |
|                                      | N/A                  | When dry | N/A         |
| NO. OF COATS                         | Typically 1 coat     |          |             |
| FLAMMABILITY                         | Non-flammable        |          |             |

When applied as part of a roof restoration, Acryloc *Mould Rid* must be over coated using the appropriate components selected from the CRC<sup>™</sup> system.

## Product Technical Data & Specifications

### ACRYLOC<sup>®</sup> RUST CONVERTER

**PRODUCT TYPE**

Preparation Products

**PACKAGING**

5L Heavy Duty Plastic Bottle

**NOMINAL WEIGHT**

6kg

Acryloc *Rust Converter* is an acid based treatment designed for chemical passivation and removal of light rust from metal surfaces. *Acryloc Rust Converter* is supplied as a concentrate and must be diluted before use.



HIGHLY CORROSIVE, Contains Phosphoric Acid 30%w/w

Acryloc *Rust Converter* removes and passivates light to medium rust on metal as part of preparation for surface repainting. It also facilitates removal of minor deposits of oil and grease as well as chemically etching the metal surface to ensure optimum adhesion of the subsequent primer coat.

**SUITABLE SUBSTRATES**

- Zinalume®
- Galvanised Iron
- Colorbond®

**APPLICATION**

- Acryloc *Rust Converter* is a highly corrosive liquid which may produce severe burns & skin irritation.
- Suitable protective clothing must be worn when handling *Rust Converter*, including rubber gloves & safety goggles

**Dilution – always add Acryloc *Rust Converter* to water, do NOT add water to the *Rust Converter*. Mix Well**

- For Chemical etching of sound metal surfaces, slowly add one (1) part Acryloc *Rust Converter* to three (3) parts clean water.
- For removal & passivation of light rust, slowly add one (1) part Acryloc *Rust Converter* to one (1) part of clean water.

NOTE: Do not use a metal container for dilution, mixing or storage – use plastic or glass.

**Disconnect rainwater collection, see page 9, Important Notes.**

Heavy rust deposits must be removed by wire wheel or sanding before application of Acryloc *Rust Converter*. The surface must be cleaned and allowed to dry before application of Acryloc *Rust Converter*. Pressure cleaning is recommended for best results.

- Apply with brush, roller, mop or scouring pad to a dry, cool surface
- Leave for minimum of 10-15 minutes to react. Agitation of the liquid into corroded areas using a plastic scourer or broom can increase effectiveness. Thoroughly Rinse off with clean water. Avoid splashing.
- The treated area should be primed with Acryloc Metal & Galv Primer within 30 minutes of the rinse water drying.

**Coverage**

10-15 m<sup>2</sup>/L in diluted form

**Clean-Up**

Clean up with water

**TECHNICAL DATA**

|                                      |   |                   |             |
|--------------------------------------|---|-------------------|-------------|
| APPEARANCE                           | Dark green liquid                       |                   |             |
| ODOUR                                | Low                                     |                   |             |
| SPECIFIC GRAVITY (NOMINAL)           | 1.1 -1.2                                |                   |             |
| THEORETICAL COVERAGE                 | 10-15 m <sup>2</sup> /L in diluted form |                   |             |
| DRY TIME (25°C & 50% RH)<br>(APPROX) | Tack Free                               | Recoat/ Overcoat  | Fully Dried |
|                                      | N/A                                     | Within 30 minutes | N/A         |

## Product Technical Data & Specifications

### ACRYLOC<sup>®</sup> PRIMERBOND

| PRODUCT TYPE | PACKAGING                   | NOMINAL WEIGHT |
|--------------|-----------------------------|----------------|
| Prime Coats  | 20L Heavy Duty Plastic Pail | 22kg           |

Acryloc *Primerbond* is a ready to use, clear drying, penetrating and binding primer.

Acryloc *Primerbond* is the recommended primer for tiled roofs as part of the Commercial Roof Coating system (CRC). Acryloc *Primerbond* is extremely effective on substrates where the surface is chalky or prone to dusting. The formulation is designed to penetrate and bind the surface while still allowing the substrate to 'breathe'.

#### SUITABLE SUBSTRATES

- Concrete roof tiles
- Fibre Cement Sheeting
- Clay and Concrete Brickwork
- Tilt panel walls
- **Unglazed** terracotta roof tiles (under a pigmented top coat)
- Aged Colorbond®
- Cement Render
- AAC (Autoclaved Aerated Concrete)

#### APPLICATION

Acryloc *Primerbond* does not require thinning or dilution

- Acryloc *Primerbond* can be applied using a roller, brush, HVLP spray equipment or airless spray equipment
- If using spray equipment, a 17 thou tip and white gun filter is recommended
- Apply Acryloc *Primerbond* liberally, allowing good penetration into the substrate. Applying excess material is acceptable providing it is not allowed to pool on the surface, as this may affect the top coat.

#### Coverage

10-12m<sup>2</sup>/L per coat on roof tiles

#### Clean-Up

Clean up with water

#### TECHNICAL DATA

|                                      |                           |                  |             |
|--------------------------------------|---------------------------|------------------|-------------|
| APPEARANCE                           | Milky white liquid        |                  |             |
| ODOUR                                | Low                       |                  |             |
| RESIN TYPE                           | Modified acrylic emulsion |                  |             |
| SPECIFIC GRAVITY (NOMINAL)           | ~1.03                     |                  |             |
| DRY TIME (25°C & 50% RH)<br>(APPROX) | Tack Free                 | Recoat/ Overcoat | Fully Dried |
|                                      | 30 mins                   | After 45         | 2 hours     |
| NO. OF COATS                         | Typically 1 coat          |                  |             |
| FLAMMABILITY                         | Non-flammable             |                  |             |

Acryloc *Primerbond* **must** be over-coated with an appropriate product from the CRC coating system

## Product Technical Data & Specifications

### ACRYLOC<sup>®</sup> METAL & GALV PRIMER

| PRODUCT TYPE | PACKAGING                   | NOMINAL WEIGHT |
|--------------|-----------------------------|----------------|
| Prime Coats  | 15L Heavy Duty Plastic Pail | 22kg           |

Acryloc *Metal & Galv Primer* is a water based coating containing inorganic rust passivators, inhibitors, adhesion promoters and inert fillers.

Acryloc *Metal & Galv Primer* is designed for priming Zinalume<sup>®</sup> and galvanised iron surfaces prior to application of subsequent topcoats.

#### SUITABLE SUBSTRATES – when properly prepared

- Zinalume<sup>®</sup>
- Galvanised Iron

#### APPLICATION

Acryloc *Metal & Galv Primer* does not require thinning or dilution

- Acryloc *Metal & Galv Primer* can be applied using a roller, brush, HVLP spray equipment or airless spray equipment
- If using spray equipment, an 18 thou tip and white gun filter is recommended
- Try to maintain a Wet Film Thickness of 100-150uM.

#### Coverage

6.5 – 10 m<sup>2</sup>/L single coat

#### Clean-Up

Clean up with water

#### TECHNICAL DATA

|                                      |                              |          |             |
|--------------------------------------|------------------------------|----------|-------------|
| APPEARANCE                           | Viscous grey coloured liquid |          |             |
| ODOUR                                | Low                          |          |             |
| RESIN TYPE                           | Modified acrylic emulsion    |          |             |
| SPECIFIC GRAVITY (NOMINAL)           | 1.3 -1.5                     |          |             |
| WET FILM THICKNESS (RECOMM)          | 100-150 microns single coat  |          |             |
| DRY TIME (25°C & 50% RH)<br>(APPROX) | Tack Free                    | Overcoat | Fully Dried |
|                                      | N/A                          | When dry | N/A         |
| NO. OF COATS                         | Typically 1 coat             |          |             |
| FLAMMABILITY                         | Non-flammable                |          |             |

Acryloc *Metal & Galv Primer* must be over-coated with Acryloc CRC.

## Product Technical Data & Specifications

### ACRYLOC<sup>®</sup> HIGH BUILD UNDERCOAT

**PRODUCT TYPE**

Undercoat

**PACKAGING**

15L Heavy Duty Plastic Pail

**NOMINAL WEIGHT**

22.5kg

Acryloc *High Build Undercoat* is a water based acrylic, self-leveling & filling undercoat, designed for application to a primed surface. The pigment in *Acryloc High Build Undercoat* assists applicators ensure complete coverage of both the *High Build Undercoat* and the subsequent coating.

Acryloc *High Build Undercoat* fills and levels the surface of weathered cement roof tiles, providing a smoother, more even surface for top coat application which improves the appearance of the finished roof coating system.

**SUITABLE SUBSTRATES**

- Primed concrete roof tiles

**APPLICATION**

Acryloc *High Build Undercoat* does not require thinning or dilution

- *Acryloc High Build Undercoat* can be applied using a HVLP spray equipment or airless spray equipment
- If using airless spray equipment, a 23-25 thou tip and white gun filter is recommended
- Try to maintain a Wet Film Thickness of 250-275 microns for a single coat.
- *Acryloc High Build Undercoat* must be over-coated with Acryloc CRC

**Coverage**

3.5-4m<sup>2</sup>/L per coat

**Clean-Up**

Clean up with water

**TECHNICAL DATA**

|                                      |                           |                  |             |
|--------------------------------------|---------------------------|------------------|-------------|
| APPEARANCE                           | Off-white, viscous liquid |                  |             |
| ODOUR                                | Low                       |                  |             |
| RESIN TYPE                           | Acrylic                   |                  |             |
| APPLICATION METHODS                  | Spray                     |                  |             |
| SPECIFIC GRAVITY (NOMINAL)           | 1.3 -1.5                  |                  |             |
| WET FILM THICKNESS (RECOMM)          | 250-275 microns per coat  |                  |             |
| DRY TIME (25°C & 50% RH)<br>(APPROX) | Tack Free                 | Recoat/ Overcoat | Fully Dried |
|                                      | 30 minutes                | 1 hour           | 2 hours     |
| NO. OF COATS                         | Typically 1 coat          |                  |             |
| FLAMMABILITY                         | Non- flammable            |                  |             |

## Product Technical Data & Specifications

### ROOFCOTE SUPA COOL

#### SYSTEM COMPONENTS

- Supa Cool Thermicoat™ Base - 13.5L in 15L Heavy Duty Plastic Pail, nominal weight 15kg  
 Supa Cool Membrane Base - 13.5L in 15L Heavy Duty Plastic Pail, nominal weight 15kg  
 Reflectacoat Tint Pacs - 1.5L Plastic Jerry Can, nominal weight 2.5kg

#### DESCRIPTION

*Roofcote Supa Cool* is a heat reflective roof membrane system, combining Thermilate® insulating ceramic beads with special ceramic pigments that reflect radiant heat.

Supa Cool is available in a range of 26 colours.

Two coats are applied to a primed roof, *Supa Cool Thermicoat* and then *Supa Cool Membrane*, both using the chosen colour of Reflectacoat Tint Pac – 1.5L of *Tint Pac* added to 13.5L of the respective Supa Cool base.

#### SUITABLE SUBSTRATES – when properly prepared

- Unglazed terracotta tiles
- Zinalume®
- Galvanised Iron
- Concrete tiles
- Colorbond®
- Fibre Cement Sheet

#### APPLICATION

- If the *Reflectacoat Tint Pac* has not been added to the base, add the full contents of the *Tint Pac* to the 13.5L of base and mix thoroughly in accordance with the directions on the *Tint Pac* label.
- A total of two (2) coats must be applied to provide the heat reflective performance.  
 The first coat required is *Supa Cool Thermicoat* – ie. Reflectacoat Tint added to Supa Cool Thermicoat base.  
 The second coat required is *Supa Cool Membrane* – ie. Reflectacoat Tint added to Supa Cool Membrane base.

#### Method

- Thinning is not normally required but up to 500mL of water can be added to 15L of coating to aid spraying.
- *Supa Cool* can be applied using a long or short nap roller, brush, pad, HVLP spray or airless spray equipment
- Apply evenly, avoid loading coating in one area as this will may cause sagging. Try to keep a 'wet edge'
- Try to maintain a Wet Film Thickness of 175-200uM for each single coat by checking regularly with a Wet Film Thickness Gauge

#### Thermicoat

- If using airless spray equipment, the gun filter should be removed for the Thermicoat otherwise the filter could strain the Thermilate beads from the coating and block up. Use a large tip, 27 to 31 thou is recommended.

#### Membrane

- If using airless spray equipment for the Membrane coat, a 21-23 thou tip and white gun filter are recommended

#### Coverage

5-5.5m<sup>2</sup>/L per coat

#### Clean-Up

Clean up with water

#### TECHNICAL DATA

|                                      |  |                  |             |
|--------------------------------------|--|------------------|-------------|
| RESIN TYPE                           | Acrylic Emulsion   |                  |             |
| APPLICATION METHODS                  | Roller, brush, spray   |                  |             |
| SPECIFIC GRAVITY (NOMINAL)           | ~1.03 (base), 1.0 -1.2 (CRC base plus Tint Pac)              |                  |             |
| WET FILM THICKNESS (RECOMM)          | 175-200 microns per coat                                     |                  |             |
| DRY TIME (25°C & 50% RH)<br>(APPROX) | Tack Free  | Recoat/ Overcoat | Fully Dried |
|                                      | 1 hour   | After 2 hours    | 24 hours    |
| NO. OF COATS                         | 2 coats, Supa Cool Thermicoat followed by Supa Cool Membrane |                  |             |

## Product Technical Data & Specifications

---

### Important Notes

Rainwater tanks must be disconnected from the guttering system before commencing work. It may also be necessary to disconnect from stormwater systems depending on local requirements –check with the appropriate local authority.

It is particularly important to prevent Heavy Duty Cleaner, Mould Rid and Rust Converter from entering drinking water systems.

The guttering must remain disconnected until after application of all coatings and until all residues are washed from the guttering as material could be split on the roof or washed off if rain falls before the coating is fully cured.

It is safe to collect drinking water once the gutter system is cleaned and the Roofcote coatings have fully cured.

While the Roofcote CRC System is suitable for Fibre Cement sheeting, special approvals and equipment are required for cleaning and coating Asbestos Cement – check with the appropriate local authority.

- Do not apply Acryloc products when rain is anticipated within 5 hours of completion of the days work, longer in damp, cold +/- humid conditions
- Avoid application on hot surfaces or in hot windy conditions
- Application should be carried out on a day with temperatures above 10°C and below 32°C

### OTHER CONSIDERATIONS

#### Shelf-Life – Unopened Pails

Maximum two (2) years from date of manufacture when stored correctly

#### Transport & Storage

Pails should not be stacked more than three high during transportation and must be transported upright.

Store in a cool place, upright, out of direct sunlight and above 4°C

---

Refer to Material Safety Data Sheets for **Acryloc products** before use.

For further information on **MSDS**, call the Acryloc **Tech – Info line** on **1300 661 745** or visit **www.acryloc.com.au**

### SAFETY & HANDLING

- Avoid inhalation of vapour, prolonged or repeated skin contact and particularly eye contact
- Wear protective clothing to minimize skin contact and wear goggles where splatter is likely
- Where spills occur, soak up liquid spillage with sand/sawdust and dispose of in a sensible manner. Do not permit run-off to sewer, storm water or open bodies of water

Full pails may be HEAVY. Wear protective footwear and seek assistance if necessary.

### FIRST AID MEASURES

#### Ingestion

If swallowed, wash out mouth with water. Do **NOT** induce vomiting. Drink at least two (2) glasses of water to dilute stomach contents. Seek medical attention.

#### Eye

Wash with copious amount of water for 15 minutes holding eyelid(s) open. Seek medical attention if symptoms persist.

#### Skin

Wash thoroughly with water

**For additional Safety & product information consult the Technical data sheets and Material Safety data sheets for the individual products.**

---

### MANUFACTURED / DISTRIBUTED BY:

Acryloc Building Products

174 Cavan Rd, DRY CREEK SA 5094

P: +61 8 8368 0222

E: [sales@acryloc.com.au](mailto:sales@acryloc.com.au)

F: +61 8 8349 4260

W: [www.acryloc.com.au](http://www.acryloc.com.au)

---