

CCS Ultra Epoxy High Build (Low VOC)

DESCRIPTION

CCS Ultra Epoxy High Build is a clear, two component 100% solids, solvent free epoxy coating system for internal concrete floors. It is classified as a low VOC (Volatile Organic Compounds) sealer.

CCS Ultra Epoxy High Build has been designed to provide a high level of chemical and abrasion resistance and is both impervious and easily cleaned.

Should a colour be desired, specially formulated tint packs can be added to the clear base and are available in the following colours:-

- White
- Beige
- Light Grey
- Mid Grey
- Dark Grey
- Black

RECOMMENDED USES

- Food and chemical processing areas
- Warehouse floors
- Polished concrete
- Hospitals and schools
- High traffic areas
-

PACKAGING

CCS Ultra Epoxy High Build is available in 10 and 20 litre kits consisting of:-

10 litre kit:-

Part A – Base – 7.5 litres

Part B – Hardener – 2.5 litres.

20 litre kit:-

Part A – Base – 15 litres

Part B – Hardener – 5 litres.

Colour Tint Packs:-

Add one colour Tint Pack per 10 litre kit.

COVERAGE RATES

Coverage is typically 4-5m² per litre per coat; however this may vary due to surface texture and porosity of the concrete. A minimum of two coats should be applied.

APPLICATION METHOD

Apply CCS Ultra Epoxy High Build with a lambswool or mohair roller, airless sprayer or gauge rake.

PREPARATION

- All surfaces to be treated should be structurally sound and all previous coatings, adhesives, efflorescence or laitance should be removed by mechanical grinding or abrasive blast cleaning, high pressure water blasting, mechanical scrubbing or other suitable means.
- Holes, nonstructural cracks and other surface deformities should be repaired using the CCS Epoxy Repair Kit and/or ACS Rapid Patch as per the technical data sheet.
- New concrete floors should be at least 28 days old before applying CCS Ultra Epoxy High Build.

FIRST COAT

1. **Using a mechanical mixer**, premix each individual component (ie: Part A and Part B) until homogenous. **Note:-** Please ensure you clean the mixer between mixing.
2. If a colour is desired, add one Tint Pack (for the 10 litre kit) or two Tint Packs (for the 20 litre kit) to the Part A – Clear Base. Stir with a **mechanical mixer** for 1-2 minutes, scraping the product downwards from the inside of the container and then **mechanically stir** for a further 1-2 minutes. **Note:-** Please ensure you clean the mixer thoroughly before commencing the next step.

3. Add the Part B-Hardener to the Part A-Base and **mechanically mix** for 1-2 minutes. Scrape product downwards from the insides of the container and **mechanically stir** for a further 1-2 minutes.
4. Leave material to stand for 2-5 minutes before application and only mix as much as is likely to be used within the pot life of the product. (ie:- the pot life is approx. 40 minutes, depending on climatic conditions).
5. Apply the first coat of CCS Ultra Epoxy High Build at a rate of 4-5m² per litre.
6. To provide a textured surface that will enhance traction, apply CCS Glass Bead to the first coat of CCS Ultra Epoxy High Build whilst still wet. Apply at a heavier rate of 4m²/litre.
7. Allow the first coat to dry for a minimum of eight hours then remove excess glass bead with a broom or an industrial vacuum.

SECOND COAT

Apply the final coat of CCS Ultra Epoxy High Build in a uniform manner. **Note:-** It is imperative that you use a clean bucket and clean mixer before commencing mixing and application of the second coat.

CLEAN UP

Wash all equipment in CCS Solvent immediately following application and mixing. Hardened material can be removed mechanically.

CURING TIME

Allow the surface to cure for at least 24 hours before subjecting it to pedestrian traffic, 72 hours before allowing vehicular traffic and 5-7 days before subjecting it to chemicals or severe abrasion.

STORAGE

Store between 10°C and 30°C away from direct sunlight. Partly used containers must be sealed tightly when not in use.

For further information consult the **Material Safety Data Sheet** and read the product label carefully before use. **Material Safety Data Sheets** are available by phoning **1800 077 744**.

Please Note:- The information given in this data sheet is based on our current knowledge of the product when properly stored, handled and applied. We cannot guarantee that the product will be suitable, effective or safe when used for any purpose other than its stated uses.

To the extent that it is lawful, we exclude warranties implied by law and limit our liability to the cost of replacing the product. We accept no responsibility for loss or injury caused by improper use, inadequate preparation, inexperienced or negligent application, or ordinary wear and tear.

Service or advice given by our staff should not amount to responsibility for the project - since the owner, or their contractor (and not River Sands), is responsible for procedures relating to the application of the product.



Concrete Colour Systems
A Division of River Sands Pty Ltd
 683 Beenleigh Redland Bay Rd,
 Carbrook Qld 4130
 Ph: 07 3287 6444 Fax: 07 3287 6445
 Toll Free Helpline: 1800 077 744
www.concretecoloursystems.com.au